

ABSTRACT

A method for etching a metal layer is described. That method comprises forming a metal layer on a substrate, then exposing part of the metal layer to a wet etch chemistry that comprises an active ingredient with a diameter that exceeds the thickness of the metal layer.